LISTING OF THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

(Previously Presented) A bistable liquid crystal device comprising:

 a first substrate having thereon a first conductive layer and a first alignment layer;
 a second substrate having thereon a second conductive layer and a second alignment layer;

a liquid crystal layer sandwiched between said first and second alignment layers, said first alignment layer inducing a first pretilt angle θ_1 in the range of 20° - 65° between said liquid crystal layer in contact with said first alignment layer, and said second alignment layer inducing a second pretilt angle θ_2 in the range of 20° - 65° between said liquid crystal layer in contact with said second alignment layer, said liquid crystal layer being capable of maintaining a stable bend state or a stable splay state at zero bias voltage and being switchable between said stable bend state and said stable splay state when a switching energy is applied in operation to said liquid crystal layer; and

at least one of said first and second alignment layers includes a mixture of vertical alignment material and horizontal alignment material.

- (Original) The device of claim 1, wherein said liquid crystal layer comprises liquid crystal having a positive dielectric birefringence when driven by electrical pulses at low frequency and a negative birefringence when driven by electrical pulses at high frequency.
 - 3. (Canceled).
 - 4. (Original) The device of claim 1 further comprising input and output polarizers.
- 5. (Original) The device of claim 4 wherein said input and output polarizers respectively angle said alignment direction by $\pm 40^{\circ}$ to $\pm 60^{\circ}$.

01013379.1 -3-

- (Original) The device of claim 1 wherein said pretilt angles on said pair of substrates are substantially different.
- (Original) The device of claim 1 wherein said pair of substrates have substantially parallel alignment directions.
- (Original) The device of claim 1 wherein said switching energy is an electrical pulse generated by said first and second conductive layers.
- (Original) The device of claim 1 wherein said switching energy is an electrical pulse having low frequency to align said liquid crystal layer to said bend state.
- 10. (Original) The device of claim 1 wherein said switching energy is an electrical pulse having high frequency to align said liquid crystal layer to said splay state.
- 11. (Original) The device of claim 1 wherein said switching energy is an electrical pulse providing an electrical field in a predetermined direction between said pair of substrates to switch said liquid crystal layer between said bend state and said splay state.
- 12. (Original) The device of claim 1 wherein one of said conductive layers further includes a patterned electrode to provide an electrical field in a predetermined direction between said pair of substrates to switch said liquid crystal layer between said bend state and said splay state.
- 13. (Original) The device of claim 1 wherein one of said conductive layers further includes a patterned electrode, said patterned electrode having an interdigital structure so that controlling the voltages on said interdigital electrode can apply either a vertical or horizontal electric field upon said liquid crystal layer.

01013379.1 -4-

- 14. (Original) The device of claim 1 wherein said first and second conductive layers are patterned into stripes that are substantially perpendicular in direction to each other to form an overlapping matrix of pixels.
- 15. (Original) The device of claim 1 wherein both said first and second conductive layers are transparent.
- 16. (Original) The device of claim 1 wherein one of said first and second conductive layer is optically reflecting.
 - 17-21. (Canceled).
- 22. (Previously Presented) A bistable liquid crystal device comprising: a first substrate having thereon a first conductive layer and a first alignment layer; a second substrate having thereon a second conductive layer and a second alignment layer; and

a liquid crystal layer sandwiched between said first and second alignment layers, said liquid crystal layer having a positive dielectric anisotropy under a low frequency electrical field and a negative dielectric anisotropy under a high frequency electrical field, said first alignment layer inducing a first pretilt angle θ_1 in the range of 20°-65° between said liquid crystal layer in contact with said first alignment layer, and said second alignment layer inducing a second pretilt angle θ_2 in the range of 20°-65° between said liquid crystal layer in contact with said second alignment layer, said liquid crystal layer

being either in a stable bend state or in a stable splay state at zero bias voltage;
being switchable between said stable bend state and said stable splay state when a
switching energy is applied in operation to said liquid crystal layer, and at least one of said first
and second alignment layers includes a mixture of vertical alignment material and horizontal
alignment material.

23. (Previously Presented) A bistable liquid crystal device comprising:

01013379.1 -5-

a first substrate having thereon a first conductive layer and a first alignment layer; a second substrate having thereon a second conductive layer and a second alignment layer; and

a liquid crystal layer sandwiched between said first and second alignment layers, said liquid crystal layer having a positive dielectric anisotropy and a cell gap-birefringence product of $0.31\pm0.1\mu\text{m}$, said first alignment layer inducing a first pretilt angle θ_l in the range of $20^\circ-65^\circ$ between said liquid crystal layer in contact with said first alignment layer, and said second alignment layer inducing a second pretilt angle θ_l in the range of $20^\circ-65^\circ$ between said liquid crystal layer in contact with said second alignment layer, said liquid crystal layer

being either in a stable bend state or in a stable splay state at zero bias voltage; being switchable between said stable bend state and said stable splay state when a switching energy is applied in operation to said liquid crystal layer, and at least one of said first and second alignment layers includes a mixture of vertical alignment material and horizontal alignment material.

01013379.1 -6-